



EPIC DC BODY COAT SELECTOR

EPIC Interior Body Coat	DC210™ High Build Epoxy	DC215™ High Build Epoxy Fast Cure	DC300™ Polyaspartic Fast Cure	DC320™ Polyaspartic Regular Cure	DC420™ Multi-Purpose High Build Epoxy	DC440™ High Build Epoxy Low Viscosity
Coverage per gallon	53-130 ft ²	50-150 ft ²	200-800 ft ²	130-300 ft ²	90-100 ft ²	150-200 ft ²
Mil Thickness	12-30	20-30	2-8	8-12	16-18	12-18
Cure Time, 70degrees ²	8-12 hrs	6-8 hrs	1-3 hrs	6-8 hrs	10-16 hrs	6-8 hrs
Finish	High Gloss	Gloss	High Gloss	High Gloss	High Gloss	Gloss
Color Options ⁴	C,F	F	C,P	C,P	C,F,P	C
Low Odor	Yes	Yes	No	Yes	Yes	Yes
Solids by Weight ³	100%	100%	85%	84%	100%	96.5
Abrasion Resistance ¹	32	26	21	15	36	36
Hardness	80 Shore D	70 Shore D	80 Shore D	55 Shore D	81 Shore D	81
VOC g/L	2	2	159	95	2	35

¹Cure Time = Coat/Topcoat

²Abrasion Resistance = Tabor CS-17 1000g @ 500 Cycles (lower value= higher resistance)

³See individual product data sheet for more information

⁴Color Options:

F= Colored at factory

P= Colored in field using pigment packs

C= Clear